



COSMO CL-300.150

*** COSMOFEN 60

Special cleaner

Examples for Application

- Removal of dust, adhesive residues of the protective film, marking pencil, rubber residues, fresh PUR foam and fresh sealant residues, as well as tar / bitumen spots
- Window and door construction for cleaning of the powder-coated and anodized aluminium and PUR sections
- Cleaning of lacquered surfaces in the plastic and metal processing industry
- Cleaning of bonding surfaces before bonding
- Removal of not cured residues of different adhesive systems

Special Properties

- Mild odour during processing
- Fast drying
- Non-dissolving

Technical Data

Basis	Mixed aliphatic hydrocarbons
Density as per EN 542 at +20 °C	approx. 0.71 g/cm ³
Processing temperatures	from +5 °C to +30 °C

Instructions for use

Acclimatise the product before the application.

Always check the surfaces to be cleaned for compatibility!

The dry, dust-free material surface is cleaned using lint-free and non-marking rags made of pulp or cotton.

If, during the cleaning process, colouring pigments can be detected in the cleaning cloth, this can also indicate that the powder coating has not cured sufficiently. In this case, also the powder coating expert should be asked.

Important instructions

Only instructed personnel in specialist firms are allowed to use the product!

Our user instructions, processing guidelines, product- and performance data, and other technical statements are only general directives; they describe only the condition of our products (values, determination of values on the date of completion) and the performances do not represent a warranty in the sense of § 443 BGB. **Because of the wide variety of applications of the individual product and the relevant special conditions (e. g., processing parameters, material characteristics, etc.), it is up to the user to test it itself;** our free expert advice for application provided in speech, writing, and as test is nonbinding.

Please, also consider the Safety Data Sheet!

Storage

Store the hermetically closed original trading units, in a dry place at temperatures of +15 °C to +25 °C no direct sun radiation.

While transported within the usual transport times, the product may be exposed to temperatures from -30 °C to +35 °C.

Storage life in unopened original packagings: 24 Months.

Packaging

1 000 ml metal bottle

10 l metal canister

30 l metal canister

200 l metal bung hole drum

Accessories

COSMO SP-870.100 - Pulp cleaning cloth

COSMO SP-810.120 - Saving humidifier/safety dispenser



Industrieverband
Klebstoffe e.V.



Weiss Chemie + Technik
GmbH & Co. KG
Hansastraße 2
D-35708 Haiger

Tel.: +49 (0) 2773 / 815 - 0
Fax: +49 (0) 2773 / 815 - 200
Email: ks@weiss-chemie.de
Web: www.weiss-chemie.de